

Decora - Plaino Supercast



Product Attributes









and Lead free

Product Description:

Ruff 'N' Tuff – Decora Plaino Supercast is a trowel applied design finish reinforced by quartz and aggregates. It is designed for fine surfaces and such specially formulated tough and water resistant exterior textured coating offers durable finish.

Recommended Usage Area:

Cement Plaster, concrete, bricks, masonry, wood, gypsum board and lime-cement plaster. For Exterior.

TECHNICAL DATA

Colour: Off White

Drying Time (at 25 ± 2 °C, Relative Humidity 60%)

• Touch dry (hrs.): 1/2 hr.

• Dry to recoat: 12 ~ 16hrs.

(Drying time may vary as per temperature, film thickness, humidity etc.)

• Gloss Level: Matt when released

• Pot Life of Thinned Material: 2 – 3 hours

Density: 1.85 ± 0.5

• VOC: Less than 50 gm/ltr

• Flash Point: NA

Theoretical Coverage*

Approx. 2.5 ~ 3.5 Sq. feet/kg/coat

* It depends on many factors like surface condition, surface roughness & porosity, surface preparation, application skill, weather conditions, dilution etc. The coverage mentioned is under ideal conditions and will vary depending on the site condition. It is recommended to establish coverage on actual site.

SURFACE PREPARATION









- **Surface Inspection** Before painting the exterior walls, undertake repairs of all surface imperfections cracks, leakages, undulations and rust caused by drainage pipes.
- Scraping & Cleaning Remove all loose paint, dirt, fungus, algae, moss and salt deposits
 alternatively by wire brushing the surface. On the fungus affected areas, apply 1 or 2 coats of
 Berger Paint Bio-Wash solution (5% v/v) by brush. Allow it to dry overnight. Wash it again next
 day with potable water thoroughly. Wash the scraped surface thoroughly and allow it to dry.
 Berger Recommended Tools Express Painting Sander with Paint Scraper attachment and
 Express Painting Jet Washer.
- Crack Bridging For filling cracks up to 5 mm use Home Shield Crack Fill Paste. For wider cracks use Home Shield Advance Latex Plus as per the product usage guidelines.
- Waterproofing If required apply Home Shield Latex Shield 2K on the affected areas as per the
 product usage guidelines. For highly affected areas Home Shield Dampstop coating system is
 recommended.



Packaging





30 Kg Drum / Bag

Shelf Life

12 months in Drum & 6 months in Bag in original sealed pack from the date of manufacture.

Recommended System



Weathercoat Exterior Primer / Seal-O-Prime / Acribond Primer

1 Coat



Ruff 'n' Tuff – Decora Plaino Supercast

1 or 2 Coats



Weathercoat (Longlife, Allguard, Antidust, Smooth)/ Outsmart/ Outshine

2 coats

Shipping Information



Freight Classification
Paint



Flammability
Non-Flammable

Flash Point - Water

HSN Code: 32091010

APPLICATION DATA

Application Method



Trowel

Thinning Recommended



Dilute max 5% if required, for better consistency

Thinner/ Cleaner



Fresh Tap Water

Overcoating time (at 25 ± 2 °C)



12 - 16 hrs.

Directions for use

Primer Application – Apply one coat of Weathercoat Exterior Primer / Seal-O-Prime / Acribond Primer as recommended and allow it to dry for 4 to 6 hours.

Texture Application – Apply one or Two coats of Plaino Supercast by Trowel. (time interval between two coats 12 to 16 hrs.)

- Recommended Tool: Trowel.
- Thinning: If required, use 3-5% of fresh water for better consistency.

Top Coat – Apply 2 coats of Berger Weathercoat (Longlife, Allguard, Antidust, Smooth)/ Outsmart/Outshine Exterior Emulsion with recommended dilution ratio as finishing coat.

Safety & Precautions

- Prior to use, read and follow product specification, MSDS and label information.
- Stir the contents thoroughly before dilution, avoid extra thinning, over extend the roller/brush.
- Do not apply when temperature is below 10°C, humidity above 90%.
- Ensure that existing paint is properly bonded and, not peeling off.
- · Avoid contact with eyes and skin.
- Use safety equipments like rubber or polythene gloves, safety goggle / glasses and face mask.
- · Keep away from children.
- Stir / Mix Well before use
- Moisture content of the wall should be ideally below 12%
- $\bullet~$ pH value of the wall surface should be ideally between 7 11.

Disclaimer

The information and the recommendations set forth in this Technical Data Sheets are based upon tests conducted by or on behalf of Berger Paints Ltd. Such information and recommendations set forth herein are subject to change without notice and pertain to the product offered at the time of publication. Consult your Berger Paints Ltd. representative for the most recent Technical Data Sheet.

Version No.: BPTEX01/06/2018. Please note that this data sheet supersedes all previous versions

